



## Product Specification Sheet

### ERT-J

# LABEL-HOUSE

Printable with resin ribbon (FTA-LH...x...) for foil labels

**Removable, glossy white polypropylene labels  
on roll for thermal transfer printers**

#### Material Thickness:

	Value (Tolerance)	Unit	Test Method
Facestock	50	micron	ISO 534
Adhesive	15	micron	ISO 534
Liner (glassine)	55	micron	ISO 534

#### Adhesive (acrylic):

		Value	Unit	Test Method
Shear Strength		*		
Initial Tack		*		
Peel Resistance	Stainless Steel	*		
	Glass	6 +/- 3	N/25 mm	FTM 1 /24h
	Polypropylene	*		
	Paint (automotive)	*		
	PBT	*		
Application Temperature		min. +5	°C	
Temperature Range (Adhesive)		-30 to +90	°C	

\*no information provided by the manufacturer

**Certifications:** Material meets REACH and RoHS requirements (2011/65/EU). Adhesive conforms to toy guideline EN 71-3. Material is solvent free. IMDS data available.

**Printability:** Suited for thermal transfer printing with resin ribbons (i.e. Armor AXR® 7+, AXR® 8; Labelident resin, Labelident Ultra resin; Zebra 4800, 5095, 5100, Coding TTR).

**Storage:** Material is stable for two years stored at max. 21°C and 50% rel. humidity. Damp conditions, excessive heat and/or cold conditions should be avoided.

**Further Information:** Resistant against high temperatures and chemical substances. Removable acrylic adhesive can be removed from most substrates without leaving residue. For new or difficult substrates, testing is recommended.

Note: All values are guidelines and not intended for use in setting specifications. The information provided does not constitute any warranty, express or implied, and is intended solely for the recipient and shall not be forwarded to any third party. The buyer of our products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application. Samples of our materials can be provided upon request. Information is subject to change without prior notification. Last Updated: January 2019.